



Technical Data Sheet  
 (Performance Characteristic)  
 Malaysian Tropical Medium Light Hardwood

Plywood Type : Low Formaldehyde Emission Concrete Forming (CP F☆☆☆☆)		12mm		15mm	
No of Plies		5		7	
Species		Medium Light Hardwood			
Panel Size		900 x 1800			
Bonding / Adhesive		Type 1 - Cycle Boiling Test Melamine Urea Formaldehyde			
Property	Test Method	Value of Test		Value of Test	
Moisture Content	JAS	11.5 %		12.0 %	
Formaldehyde Emission	JAS	0.35 mg/L		0.38 mg/L	
Bonding Quality (Shear Strength)	JAS	2.1 Mpa	Requirement ≥ 0.7MPa	1.7 Mpa	Requirement ≥ 0.7MPa

This performance characteristic is according to the standard JAS