



Technical Data Sheet (Performance Characteristic) Floor Base Plywood

Plywood Thickness :			9 mm		11.7 mm		
Species			Malaysian Medium Light Hardwood				
Panel Size			965mm x 1840mm				
No of Plies			5		7		
Bonding / Adhesive			Phenol Formaldehyde				
Property		Test Method	Value of Test				
Moisture Content		EN 322	7.0 – 12.0 %				
Density		EN 323	500-650 kg/m³				
Formaldehyde Emission		JAS 2018	≤ 0.4 mg/L (F4*)				
Modulus of Elasticity (MOE)	Parallel	Young Modulus (Gpa)	JAS 2018	5.4 – 6.9 N/mm²		4.9 – 6.4 N/mm²	
		Bending Strength (Mpa)		25.0 – 1.0 N/mm²		21.0 – 27.0 N/mm²	
	Perpendicular	Young Modulus (Gpa)		2.1 – 3.4 N/mm²		2.4 – 3.9 N/mm²	
		Bending Strength (Mpa)		13.0 – 19.0 N/mm²		17.0 – 20.0 N/mm²	
Bonding Quality (Shear Strength)		JAS 2018	≥ 0.7 N/mm²				

This performance characteristic is according to the standard BS13986:2004 + A1:2015 & JAS2018.
All figures shown in the report revealed the physical properties of sample plywood, not necessarily the actual plywood you received

Prepared by:

izati

Nor Izati
Lab Personnel

Date: 02/05/2025